

PROPRIETATI MECANICE

Grup Otel	Conditii livrare	Rezistenta la intindere	Limita la cedare	Elongatie
		N/mm²	N/mm²	%
St35, E235, OLT35	BK(+C) BKS(+SR) NBK(+N)	min 480 min 420 340÷480	- min 350 min 235	min 6 min 16 min 25
St45, OLT45	BK(+C) BKS(+SR) NBK(+N)	min 580 min 520 440÷570	- min 375 min 255	min 5 min 12 min 21
St52, E355, OL52.3k	BK(+C) BKS(+SR) NBK(+N)	min 640 min 580 490÷630	- min 450 min 355	min 4 min 10 min 22
E410, STE460	BKS +N	min 690 550÷700	min 590 min 410	min 12 min 22