

Propertati Mecanice

Grup Otel	Rezistenta la intindere	Limita la cedare min.	Elongatie
	MPa	MPa	%
St33.2, OL32, OL37, OL44	290÷510	185	18
Fe 330	330÷520	210	22
S195T	320÷520	195	20