

Proprietati Mecanice

Grup Otel	Rezistenta la intindere	Limita la cedare min.	Elongatie min .	Impact Energie Min.	
	MPa	MPa	%	J	°C
P215NL	360÷480	215	25	40	-40
P265NL	410÷570	265	24	40	-40
Grade 6	min. 415	240	30	18	-45