

## Proprietati Mecanice

<b>Grup Otel</b>	<b>Rezistenta la intindere</b>	<b>Limita la cedare min.</b>	<b>Elongatie</b>	<b>Impact Energie Min.</b>	
	<b>PSI (MPa)</b>	<b>PSI (MPa)</b>	<b>%</b>	<b>J</b>	<b>°C</b>
Grade A, L210GA	min.48000(331)	min 30000(207)	conform grosimii peretilor		
Grade B, L245GA	min.60000(414)	min.35000(241)			
L245NB	415	245÷440	22	60	0
L290NB	415	290÷440	21	60	0
L360NB	460	360÷510	20	60	0
L415NB	520	415÷565	18	60	0