

**Tab.1 TEVI MECANICE LAMINATE LA RECE conform. DIN 2448**

WT	mm	2	2.3	2.6	2.9	3.2	3.6	4	4.5	5	5.6	6.3	7.1	8	8.8	10	11	12.5		
	in	0.079	0.091	0.102	0.114	0.126	0.142	0.157	0.177	0.197	0.220	0.248	0.280	0.315	0.346	0.394	0.433	0.492		
OD	lungime max (m)																			
mm	in																			
16	0.630	10	10	10	10	10	10													
19	0.749	10	10	10	10	10	10													
20	0.787	10	10	10	10	10	10	10												
21.3	0.839	10	10	10	10	10	10	10	10											
25	0.984	10	10	10	10	10	10	10	10	10										
25.4	1.000	10	10	10	10	10	10	10	10	10										
26.9	1.059		10	10	10	10	10	10	10	10	10									
30	1.181		12	12	12	12	12	12	12	12	12	12	12	12						
31.8	1.252		12	12	12	12	12	12	12	12	12	12	12	12						
33.7	1.327		12	12	12	12	12	12	12	12	12	12	12	12						
38	1.496				12	12	12	12	12	12	12	12	12	12	12	12				
42.4	1.669					12	12	12	12	12	12	12	12	12	12	12				
44.5	1.752					12	12	12	12	12	12	12	12	12	12	12				
48.3	1.902					12	12	12	12	12	12	12	12	12	12	12				
51	2.008					11	11	11	11	11	11	11	11	11	11	11				
54	2.126					10	10	10	10	10	10	10	10	10	10	10	10	10	10	
57	2.244						9	9	9	9	9	9	9	9	9	9	9	9	9	
60.3	2.374						9	9	9	9	9	9	9	9	9	9	9	9	9	
63.5	2.500							9	9	9	9	9	9	9	9	9	9	9	9	
70	2.756								9	9	9	9	9	9	9	9	9	9	9	
73	2.874										9	9	9	9	9	9	9	9	9	
76.1	2.996										9	9	9	9	9	9	9	9	9	
82.5	3.248										9	9	9	9	9	9	9	9	9	
88.9	3.500											9	9	9	9	9	9	9	9	
95	3.740												9	9	9	9	9	9	9	
101.6	4.000													9	9	9	9	9	9	
108	4.252														9	9	9	9	9	

**Note:** 1. Marimi intermediere pot fi produse inainte de comanda;

2. Greutate  $We=10.68 (OD-WT)xWT$ , [lbs/ft]

$We=0.0246615x(OD-WT)xWT$ , [kg/m];

3. Tevi mecanice conform DIN 1629, DIN1630, nu acopera cerere de suprafata si marime de precizie pentru DIN 2391.

Pentru aceste tevi rugam sa consultati Programul de precizie